

DESCRIPTION

A polyether polyurethane foam which meets the requirements of Schedule 1 Part 1 of The Furniture and Furnishings (Fire) (Safety) Regulations.

TYPICAL PHYSICAL PROPERTIES

Physical properties are measured using test methods described in BS EN ISO 845:1995. (Determination of Density), BS EN ISO 2439 (Determination of Hardness) and BS EN ISO1798 (Determination of Tensile Strength and Elongation) and BS EN ISO1856 (Determination of compression).

Piece Density Range	32-34 kg/m³
Hardness (40%) Strength	155-195N
Nominal Tensile Strength	Min 50kPa.
Nominal Elongation at Break	Min 90%.
Nominal Compression Set	Max 12%

Standard colour is blue.

Vitafoam reserve the right to update product data information without prior notice.
Issued 05/2018

For product samples and to find out more about how you could utilise Vitafoam's unique properties, contact us:

T: 0161 655 2744

E: info@vcfuk.com

www.vitafoam.co.uk



Registered Office:
Oldham Road,
Middleton,
Manchester,
M24 2DB

Company Reg No: 621497