

DESCRIPTION

A Viscoelastic, temperature sensitive foam for use in heavy duty mattress and medical seating applications. Complies with the requirements of Schedule 1, Part 1, The Furniture and Furnishings (Fire) (Safety) Amended Regulations 1989.

TYPICAL PHYSICAL PROPERTIES

Physical properties are measured using test methods described in BS EN ISO2439, BS EN ISO 845, BS EN ISO 1798, BS EN ISO 8307 and in house test methods.

Nominal Piece Density Range	58-62 kg/m³
Nominal Hardness (40%) Strength	100-130N
Nominal Tensile Strength	90 kPa min.
Nominal Elongation at Break	120%.
Resilience	14% max.
Recovery rate	5-20 secs.
Compression Set	10% max.

Standard colour is blue.

Vitafoam reserve the right to update product data information without prior notice.
Issued 11/2014

For product samples and to find out more about how you could utilise Vitafoam's unique properties, contact us:

T: 0161 655 2705

E: info@vcfuk.com

www.vitafoam.co.uk



Registered Office:
Oldham Road,
Middleton,
Manchester,
M24 2DB

Company Reg No: 621497