

### DESCRIPTION

A speciality viscoelastic, temperature sensitive foam, made using raw material from renewable resources. Complies with the requirements of Schedule 1, Part 1, The Furniture and Furnishings (Fire) (Safety) Amended Regulations 1989.

### TYPICAL PHYSICAL PROPERTIES

Physical properties are measured using test methods described in BS EN ISO2439, BS EN ISO 845:1995, BS EN ISO 1798, BS EN ISO 8307 and in house test methods.

<b>Nominal Piece Density Range</b>	<b>48-52 kg/m<sup>3</sup></b>
<b>Nominal Hardness (40%) Strength</b>	<b>70-100N</b>
<b>Nominal Tensile Strength</b>	<b>Min 50 kPa.</b>
<b>Nominal Elongation at Break</b>	<b>Min 150%.</b>
<b>Resilience</b>	<b>16% max.</b>
<b>Recovery rate</b>	<b>5-30 secs.</b>

Standard colour is beige.

Vitafoam reserve the right to update product data information without prior notice.  
Issued 11/2014

For product samples and to find out more about how you could utilise Vitafoam's unique properties, contact us:

**T: 0161 655 2705**

**E: [info@vcfuk.com](mailto:info@vcfuk.com)**

**[www.vitafoam.co.uk](http://www.vitafoam.co.uk)**



Registered Office:  
Oldham Road,  
Middleton,  
Manchester,  
M24 2DB

Company Reg No: 621497