

DESCRIPTION

A flexible polyurethane foam having inherent static control properties, which is suitable for electronics packaging applications.

TYPICAL PHYSICAL PROPERTIES

Physical properties are measured using test methods described in BS EN ISO 845:1995, BS EN ISO 2439, BS EN ISO 1798 and BS EN ISO 1856.

Nominal Piece Density Range	20-23 kg/m³
Nominal Hardness (40%) Strength	100-150N
Nominal Tensile Strength	Min 70 kPa.
Nominal Elongation at Break	Min 150%.
Compression Set	Max 10%
Surface Resistivity	Max 1x10¹¹ Ohms/Sq

Standard colour is pink.

Vitafoam reserve the right to update product data information without prior notice.
Issued 11/2014

For product samples and to find out more about how you could utilise Vitafoam's unique properties, contact us:

T: 0161 655 2705

E: info@vcfuk.com

www.vitafoam.co.uk



Registered Office:
Oldham Road,
Middleton,
Manchester,
M24 2DB

Company Reg No: 621497